



[www.btm.co](http://www.btm.co)

Bituminous Waterproofing Membranes Co.  
Kemalpaşa Org. San. Bölgesi Mah. Gazi Bulvarı. No:  
152 Kemalpaşa / İZMİR / TURKEY  
Tel:+90 0232 877 04 02 (8 line)  
Fax: +90 0232 877 04 10

## PRODUCT DATA SHEET



TS EN 13707

### ELASTOSELF MD

Document number :PDS-060-4  
Publication Date :05th,Jan.2009 Revision date : 17th.Jul.2017

<b>PRODUCT DESCRIPTION</b>	Elastomeric modified bituminous waterproofing membrane.			
<b>USAGE</b>	Used for water profing of terraces and roofs			
<b>APPLICATION METHOD</b>	Self-adhesive			
<b>TOP SURFACE</b>	PE			
<b>BOTTOM SURFACE</b>	Siliconized film			
<b>REINFORCEMENT TYPE</b>	Polyester			
<b>STORAGE</b>	Rolls to be stored upright and away from heat.			
<b>ECOLOGICAL DATA</b>	Can be used in natural atmosphere			
TEST	METHOD	UNIT	TOLERANCE	VALUES
Visible defects	TS EN 1850-1	-	-	NONE
Length	TS EN 1848-1	m	-0,03	20
Width	TS EN 1848-1	m	-0,02	1
Thickness	TS EN 1849-1	mm	min.	1,5
Tensile Strength (Longitudinal)	TS EN 12311-1	N/50mm	-%0 ; +%30	500
Elongation at break (Longitudinal)	TS EN 12311-1	%	(-0 ; +20)	30
Tensile Strength (Transverse)	TS EN 12311-1	N/50mm	-%0 ; +%30	300
Elongation at break (Transverse)	TS EN 12311-1	%	(-0 ; +20)	30
Flexibility at low temperature	TS EN 1109 (top surface)	°C	min.	-15
	TS EN 1109 (bottom surface)	°C	min.	-15
Softening point	TS EN 1427	°C	min.	115

NPD = (No performance defined)

\* For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet

The manufacturer serves the right to modify, at any time, the characteristics of its products

BF/14-17-0