



[www.btm.co](http://www.btm.co)

Bituminous Waterproofing Membranes Co.  
Kemalpaşa Org. San. Bölgesi Mah. Gazi Bulvarı. No:  
152 Kemalpaşa / İZMİR /TURKEY  
Tel:+90 0232 877 04 02 (8 line)  
Fax: +90 0232 877 04 10

## PRODUCT DATA SHEET



# KİREMİTALTI KC 2000

TS EN 13859-1

Document number : PDS-057-0

Publication Date :01th,Aug.2010 Revision date : -

<b>PRODUCT DESCRIPTION</b>		Oxidized bitümen waterproofing membrane			
<b>USAGE</b>		Used as underlay for discontinuous roofing (tiles) for waterproofing			
<b>APPLICATION METHOD</b>		Mechanically fixed by nails - Please refer to application booklet			
<b>TOP SURFACE</b>		Polyethylene Film			
<b>BOTTOM SURFACE</b>		Polyethylene Film			
<b>COATING TYPE</b>		Fiberglass			
<b>STORAGE</b>		Rolls to be stored upright and away from heat.			
<b>ECOLOGICAL DATA</b>		Can be used in natural atmosphere			
TEST	METHOD	UNIT	TOLERANCE	VALUES	
Visible defects	TS EN 1850-1	-	-	None	
Length	TS EN 1848-1	m	Min.	10	
Width	TS EN 1848-1	m	. -%0,5; +%1.5	1	
Straightness	TS EN 1848-1	mm/m	Max.	3	
Mass per unit area	TS EN 1849-1	gr/m <sup>2</sup>	±%10	2000	
Tensile Strength (Transverse)	TS EN 12311-1	N/50mm	. -%0; +%30	300	
Tensile Strength (Longitudinal)	TS EN 12311-1	N/50mm	. -%0; +%30	400	
Elongation at break (Transverse)	TS EN 12311-1	%	(-0 ;+5)	2	
Elongation at break (Longitudinal)	TS EN 12311-1	%	(-0 ;+5)	2	
Resistance to water penetration	TS EN 1928 Metod A (2kPA)	Class	-	W1	
Resistance to tearing (Transverse)	TS EN 12310-1	N	±%30	140	
Resistance to tearing (Longitudinal)	TS EN 12310-1	N	±%30	120	
Dimensional Stability	TS EN 1107-1	%	Max.	0,5	
Flexibility at low temperature	TS EN 1109	°C	Min.	0	
After artificial ageing	Tensile Strength (Transverse)	TS EN 13859-1 Annex C, TS EN 12311-1	N/50mm	. -%0; +%30	300
	Tensile Strength (Longitudinal)	TS EN 13859-1 Annex C, TS EN 12311-1	N/50mm	. -%0; +%30	400
	Elongation at break (Transverse)	TS EN 13859-1 Annex C, TS EN 12311-1	%	(-0 ;+5)	2
	Elongation at break (Longitudinal)	TS EN 13859-1 Annex C, TS EN 12311-1	%	(-0 ;+5)	2
	Resistance to water penetration	TS EN 13859-1 Annex C, TS EN 1928 Method A	Class	-	W1
Reaction to fire	TS EN 13501-1	Class	-	E	
Dangerous substances	-	-	-	None	

NPD = (No performance defined)

\* For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet

The manufacturer serves the right to modify, at any time, the characteristics of its products

BF/14-17-0