



PRODUCT DATA SHEET

www.btm.co

Bituminous Waterproofing Membranes Co.
Kemalpaşa Org. San. Bölgesi Mah. Gazi Bulvarı. No:
152 Kemalpaşa / İZMİR /TURKEY
Tel:+90 0232 877 04 02 (8 line)
Fax: +90 0232 877 04 10



PLASTOBİT PP 5000 M

TS EN 13707

Document number :PDS-137-06

Publication Date :03th,Jun.2013 Revision date : 01th.Mar.2022

| PRODUCT DESCRIPTION | Plastomeric modified bituminous waterproofing membrane. | | | |
|---|---|-------------------|-------------|--------|
| USAGE | Used as top layer to waterproof terraces and roofs. | | | |
| APPLICATION METHOD | Torched. Please refer to application booklet. | | | |
| TOP SURFACE | Mineral | | | |
| BOTTOM SURFACE | Polyethylene Film | | | |
| COATING TYPE | Polyester | | | |
| STORAGE | Rolls to be stored upright and away from heat. | | | |
| ECOLOGICAL DATA | Can be used in natural atmosphere | | | |
| TEST | METHOD | UNIT | TOLERANCE | VALUES |
| Visible defects | TS EN 1850-1 | - | - | NONE |
| Length | TS EN 1848-1 | m | -0,03 | 8 |
| Width | TS EN 1848-1 | m | -0,02 | 1 |
| Straightness | TS EN 1848-1 | - | - | PASS |
| Unit of weight | TS EN 1849-1 | kg/m ² | ±0,2 | 6 |
| Watertightness | TS EN 1928 (metod A 10kPa) | - | - | PASS |
| Reaction to fire | TS EN 13501-1 | class | - | E |
| External Fire Performance | TS ENV 1187 TS EN 13501-5 | class | - | Broof |
| Shear resistance of joint | TS EN 12317-1 | N/50mm | ±30% | 800 |
| Water vapour transmission properties | TS EN 1931 | - | min. | 20.000 |
| Tensile Strength (Longitudinal) | TS EN 12311-1 | N/50mm | -%10 ; +%50 | 800 |
| Elongation at break (Longitudinal) | TS EN 12311-1 | % | (-0 ; +20) | 35 |
| Tensile Strength (Transverse) | TS EN 12311-1 | N/50mm | -%10 ; +%50 | 600 |
| Elongation at break (Transverse) | TS EN 12311-1 | % | (-0 ; +20) | 35 |
| Resistance to Impact | TS EN 12691 (metod A) | mm | min. | 1250 |
| Resistance to static loading | TS EN 12730 (metod B) | kg | min. | 20 |
| Resistance to tearing (Longitudinal) | TS EN 12310-1 | N | ±50% | 250 |
| Flexibility at low temperature | TS EN 1109 (top surface) | °C | min. | -10 |
| | TS EN 1109 (bottom surface) | °C | min. | -10 |
| | Artificial aging (EN 1296) | °C | -0 ;+10 | -10 |
| Flow resistance at elevated temperature(<2mm) | TS EN 1110 | °C | min. | 120 |
| | Artificial aging (EN 1296) | °C | -10 ;+0 | 120 |
| Dimensional stability | TS EN 1107-1 | % | max. | 0,6 |
| Adhesion of granuls | TS EN 12039 | % | max. | 30 |
| Dangerous substances | Doesn't contain asbestos or coal tar constituents. | | | |

NPD = (No performance defined)

* For information and advice on the safe handling,storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet

The manufacturer serves the right to modify, at any time, the characteristics of its products

BF/14-17-0