



www.btm.co

Bituminous Waterproofing Membranes Co.
Kemalpaşa Org. San. Bölgesi Mah.
Gazi Bulvarı. No: 152 Kemalpaşa /
İZMİR /TURKEY
Tel:+90 0232 877 04 02 (8 line)
Fax: +90 0232 877 04 10

PRODUCT DATA SHEET



POLPAN

- Channel 150

Rough

TS EN 13164

Document number : PDS-071-1

Publication Date :25th,Jan.2011 Revision date : 10th,July.2013

PRODUCT DESCRIPTION	Extruded Polystrene (XPS) Thermal Insulation Board in characteristic yellow colour- Wall type					
USAGE	Both sides of Polpan board are either unskinned and/or grooved, to provide better adherence to walls and plasters.Polpan boards are applied over ceilings, walls, columns, beams, cantilevers from the inside with adhesive and/or dowels.					
APPLICATION METHOD	Generally cement mortar adhesive and dowels are used to fix the boards to the walls and ceilings.					
STORAGE	Bundles stored away from direct sunlight					
ECOLOGICAL DATA	Can be used in natural atmosphere					
TEST	METHOD	UNIT	TOLERANCE	VALUES		
THICKNESS	TS EN 823	mm	T1	30	40	50
THERMAL RESISTANCE (R _D)	TS EN 12667 / TS EN 12939	m ² °K/W	Min.	0,85	1,10	1,40
THERMAL CONDUCTIVITY (λ _D)	TS EN 12667 / TS EN 12939	W/m °K	Max.	0,035		
LONG TERM WATER ABSORPTION	TS EN 12087	%	-	WL(T)1,5		
VISIBLE DEFECTS	TS 11989 EN 13164	-	-	NONE		
COMPRESSIVE STRENGTH	TS EN 826	kPA	Min.	CS (10/Y)100 Min.150		
DEFORMATION UNDER SPECIFIED TEMPERATURE AND MOISTURE (at 23±2°C and 90±5 moisture)	TS EN 1604	%	Min.	2		
DEFORMATION UNDER SPECIFIED TEMPERATURE AND LOAD	TS EN 1604	%	Min.	DLT(1)5 DLT(2)5		
FIRE RESISTANCE	TS EN 13501-1	-	-	E		
DIMENSIONS-WIDTH	TS EN 822	mm	±8	600		
DIMENSIONS-LENGTH	TS EN 822	mm	±10	1250		
FREZE-THAW STRENGTH	TS EN 12091	%	-	FT2		
SQUARENESS	TS EN 824	mm/m	Max.	5		
FLATNESS	TS EN 825	mm	Max.	14		

NPD = (No performance defined)

* For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet

The manufacturer serves the right to modify, at any time, the characteristics of its products

BF/14-17-0