



PRODUCT DATA SHEET

www.btm.co

Bituminous Waterproofing Membranes Co.
Kemalpaşa Org. San. Bölgesi Mah. Gazi Bulvarı. No:
152 Kemalpaşa / İZMİR /TURKEY
Tel:+90 0232 877 04 02 (8 line)
Fax: +90 0232 877 04 10



TS EN 13707

RENOVA DUE

Document number :PDS-121-04
Publication Date :01st,Dec.2012 Revision date : 23th.May.2018

PRODUCT DESCRIPTION	Elastomeric modified bituminous self adhesive waterproofing membrane			
USAGE	For terraces, roofs and foundations first layer and paste the second layer, is used for waterproofing			
APPLICATION METHOD	All surfaces must be smooth, dry, clean and free of oil, grease, rust and other foreign materials. Deep cracks, fissures and very rough surfaces should be filled with bitumen repair mastic. Bitumen primer application is recommended before usage. Before using in low temperature conditions (below 10°C), adhesion will be improved by gently warming tape and surface with warm air blower during application. Please refer to application booklet.			
TOP SURFACE	Self adhesive layer / Siliconized film			
BOTTOM SURFACE	Self adhesive layer / Siliconized film			
COATING TYPE	Polyester			
STORAGE	Rolls should be stored 5-25°C in temperature, in dry, ventilated, closed area, and max 1 year since production date. Rolls must be protected from water, frost and heavy weather conditions.			
ECOLOGICAL DATA	Can be used in natural atmosphere			
TEST	METHOD	UNIT	TOLERANCE	VALUES
Visible defects	TS EN 1850-1	-	-	NONE
Length	TS EN 1848-1	m	-0,03	10
Straightness	TS EN 1848-1	-	-	PASS
Width	TS EN 1848-1	m	-0,02	1
Thickness	TS EN 1849-1	mm	±0,2	3
Watertightness	TS EN 1928 (method A 10kPa)	-	-	PASS
Reaction to fire	TS EN 13501-1	class	-	E
Tensile Strength (Longitudinal)	TS EN 12311-1	N/50mm	-%10 ; +%50	700
Elongation at break (Longitudinal)	TS EN 12311-1	%	(-0 ; +20)	60
Tensile Strength (Transverse)	TS EN 12311-1	N/50mm	-%10 ; +%50	550
Elongation at break (Transverse)	TS EN 12311-1	%	(-0 ; +20)	60
Resistance to tearing (Longitudinal)	TS EN 12310-1	N	±30%	150
Flexibility at low temperature	TS EN 1109 (top surface)	°C	min.	-20
	TS EN 1109 (bottom surface)	°C	min.	-20
	TS EN 1296 (After artificial ageing)	°C	(-0 ; +10)	-20
Flow resistance at elevated temperature(<2mm)	TS EN 1110	°C	min.	110
	TS EN 1296 (After artificial ageing)	°C	(-10 ; +0)	110
Dangerous substances	Doesn't contain asbestos or coal tar constituents.			

NPD = (No performance defined)

* For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet

The manufacturer serves the right to modify, at any time, the characteristics of its products

BF/14-17-0